

Suelos tienda



Calidad-Quality Color-Colour Espesor-Thickness	Hoja flexible PVC sin ftalatos-Flexible PVC sheet without phthalates Gris-Grey / Negro-Black 0,300 mm
--	---

Composición: Composition:	Base resina PVC, plastificantes DOTP, Estabilizantes Ba/Zn, pigmentos orgánicos e inorgánicos PVC base resin, plastiziers DOTP, stabilizers Ba/Zn, organic and inorganic pigments.
------------------------------	---

	Método Test method	Unidades Units		Urdimbre Warp	Trama Weft
--	-----------------------	-------------------	--	------------------	---------------

Densidad Density		g/cm3	1,380		
Dureza Hardness	DIN 53505	Shore A	84-86		
Peso metros cuadrados: Weight Square meter:	gr/m2				390 grs ± 8%
Ancho de bobina: Width roll:	cm				160
Metros bobina Roll meters:	m				100
Peso bobina: Weightn roll:	Kg				66
Resistencia a la tensión Tensile strength		MPa		16-18	15-17
Alargamiento a la rotura Elongation at break	DIN 53455	%		170-190	200-215
Resistencia al rasgado Tear Strength	DIN 53363	N/mm		200-215	145-165
Punto de rotura en frío Cold crack Temp.	DIN 53372	°C	- 37		
Tolerancia de galga Gauge tolerance		%	±15		
Tolerancia de ancho Width tolerance		mm	±15		
Resistencia a la abrasión Strenght abramer	Cycle Martindale		> 40.000		
Resistencia rayos Uv: Ultraviolet resistant:	Weather meter mach.	OK			
Contracción: Contraction:		%	4		
Comportamiento al fuego Fire behaviur:			M4		

Normativa: Normative:	La suma de los niveles de concentración Pb,Cd, Hg y Cr hexavalente no excede de las cantidades mínimas establecidas en la Directiva 94/62/CE de envases y residuos de envase. The sum of the concentration levels Pb, Cd, Hg y Cr hexavalent, does not exceed the minimum amounts laid down in Directive 94/62/CE about packaging and packaging waste.
--------------------------	---

Esta información esta basada en los resultados de experiencias y test , y suministrada como guía.

This information is based on results from experience and tests and given to be used as guideline.

15.09.2022